



NOTE:

1. Base shall be 11 inches of base rock (LBR 100 min.) compacted to 98% max density per AASHTO T-180.
Alternate: 7 inches of asphalt base course may be used.
2. Alternative pavement section having a minimum total structural number of 2.82 may be utilized, as approved by Town Engineer.



TOWN OF JUPITER
ENGINEERING DIVISION
 210 MILITARY TRAIL
 JUPITER, FLORIDA 33456
 (561) 746-5134

PAVEMENT WIDENING
w/ Asphalt Milling & Overlay
DETAIL AND REQUIREMENTS

K:\Drawings\details\2007\112c - mill N widening th-in.dwg

DETAIL NUMBER

112c

Revised 20070402